

Toll Free: 87 PERMATEX (877-376-2839)

10 Columbus Blvd., Hartford, Connecticut 06106

6875 Parkland Boulevard, Solon Ohio 44139

S.I.N.: 834-300

# **Technical Data Sheet**

# Permatex<sup>®</sup> PermaPoxy<sup>™</sup> Clear General Purpose Epoxy Products

INDUSTRIAL

# PRODUCT DESCRIPTION

Permatex® PermaPoxy™ products are two part, clear epoxy adhesive systems. PermaPoxy™ Clear General Purpose epoxies are of a maximum strength formula that is available in several working times. PermaPoxy™ is ideal for complex, multi-piece assemblies. They are water and solvent resistant and available in dual syringes or tubes.

### **PRODUCT BENEFITS**

- Will not shrink
- Various curing cycles
- No clamping needed
- Fills gaps
- Nearly colorless
- Impact resistant
- Water resistant

#### **TYPICAL APPLICATIONS**

To bond rigid materials including:

- Chrome
- Fiberglass
- Glass
- Plastic
- Metal

## **DIRECTIONS FOR USE**

- 1. Protect work area from accidental spills.
- 2. Surface must be clean, dry and free of grease & oil.
- 3. Roughen surfaces with sandpaper or other abrasives.
- 4. Use a sharp blade to cut off the tips of both nozzles.
- 5. Depress plunger on syringe or squeeze out of tubes equal amounts of resin and hardener from tubes. Thoroughly mix resin and hardener on a clean discardable surface for at least one (1) minute (20 to 25 seconds in the case of the one minute epoxy) or until uniform in color.
- Apply to surfaces being repaired. Assemble parts immediately. Remove excess epoxy immediately.
- 7. Allow bond to set for the fixture time before moving.

### For Cleanup

- For any cleanup, use isopropyl alcohol before the material is allowed to dry.
- 2. Clean hands with Permatex® Fast Orange® hand cleaner or soap and water.

	Typical Value
Chemical Type	Epoxy and Mercaptan or Amine
	Resins
Mix ratio (volume)	1:1
Appearance	
Resin	Clear
Hardener	Clear
Odor	Mild
Specific Gravity	1.10 - 1.17
Flash Point, TCC	>200°F
Viscosity	Heavy syrup

### **CURING PROPERTIES**

	Working Time	<u>Fixture Time</u>
84160	50-60 seconds	2 – 4 minutes
84101	4 – 5 minutes	8 – 10 minutes
84104	40-45 minutes	60-70 minutes
84107	30-35 minutes	45-50 minutes
84201	4 – 5 minutes	8 – 10 minutes
84204	40-45 minutes	60-70 minutes

Final color Clear

Temperature range -60°F to +180°F

#### **GENERAL INFORMATION**

This product is not recommended for use in pure oxygen and/or oxygen rich systems and should not be selected as a sealant for chlorine or other strong oxidizing materials. For safe handling information on this product, consult the Material Safety Data Sheet, (MSDS).

#### ORDERING INFORMATION

Part Number	Container Size
84160	1 min. general purpose epoxy,
	0.84 fl. oz. dual syringe, carded
84101	5 min. general purpose epoxy,
	0.84 fl. oz. dual syringe, carded
84104	45 min. general purpose epoxy,
	0.84 fl. oz. dual syringe, carded
84107	30 min. crystal clear epoxy,
	0.84 fl. oz. dual syringe, carded
84201	5 min. general purpose epoxy,
	2 – 1oz. tubes, carded
84204	45 min. general purpose epoxy,
	2 – 1oz. tubes, carded

# PROPERTIES OF UNCURED MATERIAL

#### STORAGE

Products shall be ideally stored in a cool, dry location in unopened containers at a temperature between 8° to 28°C (46° to 82°F) unless otherwise labeled. Optimal storage is at the lower half of this temperature range. To prevent contamination of unused product, do not return any material to its original container.

### NOTE

The data contained herein are furnished for information only and are believed to be reliable. We cannot assume responsibility for the results obtained by others over whose methods we have no control. Permatex, Inc. specifically disclaims all warranties expressed or implied, including warranties of merchantability or fitness for a particular purpose, arising from sale or use of Permatex, Inc. products and disclaims any liability for consequential or incidental damages of any kind, including lost profits. This product may be covered by one or more United States or foreign patents or patent applications.



SPI Supplies 206 Garfield Avenue, West Chester, PA 19380, USA