



Brayco™ 1624

Perfluoroether Lubricating Oil

Description

Castrol Brayco™ 1624 is a clear, colorless perfluoroether oil. It is odorless, non-flammable, and generally chemically inert. It exhibits good thermal stability and is compatible with most commonly used propellants, fuels, and oxidizers. This product has excellent lubricating properties, good dielectric properties, excellent shear stability, and low toxicity. Brayco IC X-100 (formerly Fluoroclean™ X100) can be used to remove this lubricant.

Application

Brayco 1624 is an excellent lubricating oil for precision bearings. This product is recommended for use as a damping fluid, flotation fluid and an electrical contacts lubricant. This product is compatible with concentrated acids and bases and does not hydrolyze or oxidize. Perfluorinated fluids, in general, exhibit excellent shelf lives due to their intrinsic inertness.

Typical Characteristics

Name	Method	Units	Brayco 1624
Specific Gravity @ 16°C / 60°F	ISO 3675 / ASTM D1298	-	1.89
Density of finished grease @ 16°C / 60°F	In-house test	lb/gallon	15.8
Kinematic Viscosity @ 100°C / 212°F	ISO 3104 / ASTM D445	mm ² /s	4.2
Kinematic Viscosity @ 40°C / 104°F	ISO 3104 / ASTM D445	mm ² /s	24
Kinematic Viscosity @ 20°C / 68°F	ISO 3104 / ASTM D445	mm ² /s	64
Kinematic Viscosity @ -29°C / -20°F	ISO 3104 / ASTM D445	mm ² /s	1,326
Kinematic Viscosity @ -40°C / -40°F	ISO 3104 / ASTM D445	mm ² /s	17,500
Kinematic Viscosity @ -54°C / -65°F	ISO 3104 / ASTM D445	mm ² /s	234,900
Viscosity Index	ISO 2909 / ASTM D2270	-	55
Evaporation Loss, 22 hrs @ 120°C / 248°F	ASTM D972	%wt	2.5
Evaporation Loss, 22 hrs @ 149°C / 300°F	ASTM D972	%wt	13
Pour Point	ISO 3016 / ASTM D97	°C/°F	-54 / -65
Acid Number	ISO 6618 / ASTM D974	mgKOH/g	0.02
Knudsen Vapour Pressure @ 20°C / 68°F	-	Pa	5.32 x 10 ⁽⁻⁴⁾
Knudsen Vapour Pressure @ 100°C / 212°F	-	Pa	0.931

Additional Information

Temperature Range

-54°C to 149°C (-65°F to 300°F)

Limitations

Brayco 1624 is compatible with all commonly utilized materials, plastics, and elastomers. It is only slightly soluble in most organic solvents and fluids other than highly fluorinated solvents. Brayco 1624, like all perfluoroether based lubricants, may be adversely affected by Lewis Acids such as aluminum chloride at elevated temperatures. Newly exposed rubbing surfaces of aluminum, titanium, or magnesium alloys may react with this product under certain conditions. Such systems should be thoroughly evaluated prior to use. Surfaces must be free of organic rust inhibitors prior to oil applications to insure proper lubrication.

Brayco™ 1624

19 Mar 2015

Castrol, the Castrol logo and related marks are trademarks of Castrol Limited, used under licence.

This data sheet and the information it contains is believed to be accurate as of the date of printing. However, no warranty or representation, express or implied, is made as to its accuracy or completeness. Data provided is based on standard tests under laboratory conditions and is given as a guide only. Users are advised to ensure that they refer to the latest version of this data sheet. It is the responsibility of the user to evaluate and use products safely, to assess suitability for the intended application and to comply with all applicable laws and regulations. Material Safety Data Sheets are available for all our products and should be consulted for appropriate information regarding storage, safe handling, and disposal of the product. No responsibility is taken by either BP plc or its subsidiaries for any damage or injury resulting from abnormal use of the material, from any failure to adhere to recommendations, or from hazards inherent in the nature of the material. All products, services and information supplied are provided under our standard conditions of sale. You should consult our local representative if you require any further information.

BP Lubricants USA Inc., 1500 Valley Road, Wayne, NJ 07470
Telephone: +1-888-CASTROL Product Information: +1-877-641-1600
www.castrol.com/en_us/b2b/home.html